

## INDUSTRIAL FINISHES

# POLYURETHANE ACCELERATOR

#### **DESCRIPTION:**

Accelerator for the 6400 Series and 6800 Series High Solids Polyurethane coating to be used for reducing dry time.

#### **MIXING RATIO:**

Add one (1) to three (3) ounces of EL-005 Accelerator per gallon of catalyzed 6400 Series or 6800 Series High Solids Polyurethane coating.

### **POT LIFE:**

When using EL-005 Accelerator Solids Polyurethane a reduction of pot life is to be expected. Mix only the amount of polyurethane to be used within a two (2) hour time period. All equipment should be thoroughly cleaned immediately after use to avoid damage from paint curing within the spray system, or on other parts where the paint is not desired.

#### **VOC CONTENT:**

Coating VOC Content: 7.98 lb/gal (958 g/l)
Material VOC Content: 7.98 lb/gal (958 g/l)
VOC Partial Vapor Pressure: 6.9 mmHg @ 20°C

**CAUTION**: Adhesion may be affected with addition of EL-005 or any other polyurethane accelerator. Please consult your Cardinal Technical Representative for further details on use of this additive.

K01RS

IMPORTANT: Warranty and Disclaimer – The performance characteristics of these product vary according to the product application, operating conditions, materials applied to or use. Since these factors can affect results, we strongly recommend that you make your own tests to determine your satisfaction whether the product is of acceptable quality, has not been affected by storage or transportation and is suitable for your particular purpose under your own operating conditions prior to using any product in full scale production. Seller warrants the products to be free from defects in materials and workmanship. SUCH WARRANTY IS EXCLUSIVE AND IS IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE. No representative of ours has authority to waive or change this provision, which applies to all sales of these products.