

TECHNICAL DATA SHEET

T353 - YL02 LS #: 1140

POLYESTER T GIC POWDER COATING SEMI GLOSS METALLIC **BRASS**

RoHS Compliant

POWDER PROPERTIES

CALCULATED SPECIFIC GRAVITY: 1.22

COVE RAGE: 79.18 SQ.FT./LB. @ 2 MILS (100% EFFICIENCY)

25 - 50 MICRONS AVERAGE PARTICLE SIZE:

STORE BELOW 80 DEGREES F, IN COOL DRY ENVIRONMENT STORAGE;

SHELF LIFE: MINIMUM OF 1 YEAR

(METAL TEMPERATURE) 10 MINUTES @ 400 DEGREES F. CURE SCHEDULE:

CURED FILM PROPERTIES

ALL TESTS WERE PERFORMED AT A FILM THICKNESS OF: 2.5 to 4.0 mils

TEST	METHOD	RANGE
GLOSS @ 60 DEGREES:	D523	25% +/-5%
DIRECT IMPACT (INCH LBS.):	D2794	100 in.lbs
INDIRECT IMPACT (INCH LBS.):	D2794	100 in.lbs
PENCIL HARDNESS:	D3363	2H
CROSS HATCH ADHESION:	D3 359B	4B
FLEXIBILITY(CONICAL MANDREL):	D1737/D522	100%

CHEMICAL AND CORROSION EXPOSURE TESTS

CHEMICAL RESISTANCE: Good to excellent resistance to most solvents, oils, acids, and alkalies. OVERBAKE RESISTANCE: Slight yellowing is evident, especially in white and pastel colors.

All tests were performed on 24 gauge Bonderite 1000 panels.

APPLICATION

This product was designed to be applied by electrostatic spray, on steel, galvanized steel, or aluminum. Most powders can be reclaimed, sieved and recycled, if proper housekeeping is maintained.

The substrate pretreatment prior to powder coating is a critical factor in developing maximum corrosion resistance and maximizing the lifetime of the product.

C.R.S. (Iron phosphate): 2 to 5 stages depending upon soil level, and quality desired. 5 to 9 stages depending upon soil level, and quality desired. C.R.S. (Zinc phosphate): Galvanized steel (Zinc phosphate): 5 to 7 stages depending on soil level, and quality desired. Galvanized steel must be degassed at 5 degrees above cure

temperature to minimize gassing.

Aluminum (Chromate): 5 stage system is normally needed. Aluminum (phosphate): 5 stage system is normally needed.

Must be overcoated with clear polyester powder coating for exterior exposure.

IMPORTANT: Warranty and Disclaimer - The performance characteristics of these products vary according to the product application, operating conditions, materials important: warranty and disclaimer – The performance characteristics of these products vary according to the product application, operating conditions, materials applied to or use. Since these factors can affect results, we strongly recommend that you make your own tests to determine your satisfaction whether the product is of acceptable quality, has not been affected by storage or transportation and is suitable for your particular purpose under your own operating conditions prior to using any product in full scale production. Seller warrants the products to be free from defects in materials and workmanship. SUCH WARRANTY IS EXCLUSIVE AND IS IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE. No representative of ours has authority to waive or change this provision, which applies to all sales of these products.

www.cardinalpaint.com

Southern California **Powder Coating Corporate Headquarters** Manufacturing 1329 Potrero Avenue tel 626.937-6767 South El Monte, CA 91733

tel 626.444.9274 fax 626.444.0382

Arizona tel 602.437.2401 Colorado tel 303.286.1876 Missouri tel 314.878.3010

Pennsylvania tel 814,728,0721 Washington State tel 425.483.5665

E10MS

Northern California Minnesota tel 408.452.8522

tel 952.469.6021

North Carolina tel 336.882.9493 tel 214.333.9801

Hong Kong tel 852.2410.8200